

#7000 PROFESSIONAL LINE SEMI-GLOSS HOUSE PAINT

1-4

DESCRIPTION:

#7000 Pro Line Acrylic Latex House & Trim Paint is a high quality, acrylic product specifically formulated for professional use. This unique product is recommended for properly primed/prepared exterior surfaces of wood and wood-based products, masonry, concrete block, stucco, metal and previously painted or stained surfaces.

SPECIAL CAUTIONS:

Do not apply directly to bare metal as it can show flash rusting. Use recommended primer as first coat.

Do not apply directly to bleeding woods (cedar, redwood and plywood) as tannins will bleed and cause discoloration. Use recommended primer.

Keep packaged material from freezing. If material has been frozen, do not stir until completely thawed. If material, when stirred after thawing, is of uniform consistency and has a suitable viscosity with no lumps, it may be used.

Do not apply when surface, air or material temperature is below 50° F. (10° C.) or expected to fall below 50° F. eight hours after application. Also, do not apply when rain is imminent.

SURFACE PREPARATION:

GENERAL - Surfaces must be clean. Remove oil and grease with paint thinner. Clean off dirt with a detergent solution and rinse with clean water. Refer to "**Surface Preparation Guide**" for more detailed instructions.

UNFINISHED SURFACES:

WOOD - Countersink or completely prime all nailheads. To prevent bleeding from tannins and dyes on woods such as cedar, redwood, and plywood, prime with Latex House Paint Primer. Primer may be tinted to approximate shade of top coat. Allow primer to dry for one hour, longer if necessary in cool weather, then putty and caulk all nail holes and cracks. Apply two full coats of topcoat.

MASONRY AND CONCRETE - New surfaces must age 30-60 days minimum prior to finishing. These surfaces, when in good condition, require no special primer. For the smoothest appearance and to prevent porosity, concrete and haydite block should be filled with Latex Block Filler. The block filler should dry overnight before it is topcoated.

If efflorescence or cement dust is present on masonry and concrete, it should be removed by etching with a 10% solution of Muriatic (Hydrochloric) Acid; wear protective goggles and rubber gloves. When etching action is complete, flush off surface with clean water and allow to dry.

To provide a firm repaintable surface, badly weathered masonry with soft crumbly mortar joints and old soft asbestos cement board or shingles should be coated with Masonry Conditioner. Allow to dry overnight before topcoating.

To remove grease and mold release compounds on new or unweathered asbestos cement board and shingles, wash with paint thinner and follow with a strong detergent washing.

IRON AND STEEL - Remove rust by sandblasting, wirebrushing or sanding. Prime with Metal Primer and allow to dry overnight before topcoating.

GALVANIZED METAL & ALUMINUM - Wire brush and sand to remove loose materials, then solvent-wipe to remove surface oils.

PRE-PRIMED HARDBOARD - Remove all dirt and contamination. Finish within 30 days after installation. A minimum two-coat system is required. Either one coat primer and one coat of topcoat; or two coats of topcoat. If siding is exposed over 30 days, the first coat must be a primer.

Originated: 4/92
Revised: 9/99

#7000 PROFESSIONAL LINE SEMI-GLOSS HOUSE PAINT

1-4

DESCRIPTION:

#7000 Pro Line Acrylic Latex House & Trim Paint is a high quality, acrylic product specifically formulated for professional use. This unique product is recommended for properly primed/prepared exterior surfaces of wood and wood-based products, masonry, concrete block, stucco, metal and previously painted or stained surfaces.

Values based on **#7000 Professional Line SG House Paint White, 826-P-700**

Weight Gallon: 9.87

Weight Solids: 38.8%

Volume Solids: 28.8%

Coverage:

@ 1 Dry Mil: 462 sq. ft./gallon

@ Spread Rate: 400 sq. ft./gallon (4.0 mils wet)

Deposits a 1.2 mil dry film

VOC (g/l): Not to Exceed 380

Viscosity: 95-100 K.U. @ 77° F.

Gloss @ 60: 25-35

Grind (Hegman): #6

DOT Class: Non-Combustible, Not Regulated

HMIS/NFPA: 1,0,0

Cure Time (Based on 70° F. & 50% R.H.):

To Touch: 30 Minutes

To Recoat: 2 Hours

Recommended Thinner: Water for clean-up and reduction for spray

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Do not take internally. Close container after each use. Use only with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN. For specific safety requirements, refer to the Material Safety Data Sheet. Protect from freezing.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.

Originated: 4/92
Revised: 9/99