

CLEAN UP:

Clean brushes with mineral spirits or V.M.&P. Naphtha. Dispose of used varnish and waste in accordance with local, state and federal regulations.

COVERAGE:

Eventone Polyurethane Varnish will cover approximately 500 square feet per gallon (47 square meters per 3.785 liters) on smooth surface. Approximate dry mil thickness of 1.1 mil at recommended spreading rate of 500 square feet per gallon. Rough surface will require more material. Add 10% when figuring material requirements for loss and wastage.

DRYING:

Optimum drying conditions are 60° F. to 90° F. (16° C. to 32° C.) at 50% R.H.

Dust Free	30-60 Minutes
To Handle	4 Hours
To Recoat	Overnight

EVENTONE INTERIOR URETHANE VARNISH

6-2

DESCRIPTION:

A polyurethane varnish with excellent clarity for durable protection. A tough, flexible, mar resistant finish for interior paneling, cabinets, trim and furniture. Eventone may be used over previously varnished or unvarnished wood surfaces.

Values based on **Eventone Interior Urethane Varnish, 0395 Gloss**

Weight Gallon: 7.43

Weight Solids: 44.2%

Volume Solids: 36.3%

Coverage:

@ 1 Dry Mil: 583 sq. ft./gallon

@ Spread Rate: 400 sq. ft./gallon (4.0 mils wet)

Deposits a 1.4 mil dry film

VOC (g/l): 497

Viscosity: 45-55 Sec. #4FC @ 77° F.

Gloss @ 60: 90+

Grind (Hegman): #6

DOT Class: Combustible, Flash Point 103°F.

Federal Specification: TT-C-540 Performance Alternate

HMIS/NFPA: 1,2,0

Cure Time (Based on 70° F. & 50% R.H.):

To Touch: 4 Hours

To Recoat: Overnight

Recommended Thinner: None. Apply at package viscosity. Mineral spirits for clean-up

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Do not take internally. Close container after each use. Use only with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN. For specific safety requirements, refer to the Material Safety Data Sheet.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.

Originated: 4/92
Revised: 9/99