

DESCRIPTION:

Supr-Covr is a premium quality alkyd-based interior enamel undercoat for use over bare wood, trim, furniture, plaster walls and previously painted surfaces. Product has excellent adhesion and will seal the most porous surfaces providing good holdout for finish coats. Supr-Covr may be topcoated with either latex or oil-based topcoats. Brush application is preferred. Roller or spray application may also be used.

Reprinted from National Paint and Coatings Association, Inc., FLAMMABILITY OF PAINT STUDY conducted by Southwest Research Institute, Project 3-3774-141. "We believe this study provides substantial evidence that conventional paints and coatings do not increase the flame spread of either non-flammable or flammable substrate upon which they are applied. It also indicates that any fuel contribution or smoke density increase is insignificant when compared with the contribution of the substrate itself."

SPECIAL CAUTIONS:

Enamel Undercoat should not be applied directly to drywall or sheet-rock because it will raise the nap of the paper fiber requiring sanding to a smooth surface before finish coat can be applied. Seal drywall with a coat of latex primer before Enamel Undercoat is applied to avoid this condition.

Do not apply when surface, air or material temperature is below 50° F. (10° C.).

SURFACE PREPARATION:

GENERAL - Surface must be clean. Remove oil and grease with a detergent solution or paint thinner. Wash off dirt with warm soapy water and rinse with fresh water. Rust should be removed by wirebrushing or sanding. Refer to "**Surface Preparation Guide**" for more detailed instructions.

UNFINISHED SURFACES:

BARE WOOD - Sand smooth and putty nail holes and cracks. Apply Enamel Undercoat and allow to dry a minimum of 16 hours. Sand lightly if necessary and apply topcoat.

PLASTER - Apply one coat of Enamel Undercoat to the cured, thoroughly aged plaster and allow to dry a minimum of 16 hours before topcoating. Sand lightly for maximum smoothness.

DRYWALL - For drywall construction where semi-gloss finishes are desired, such as bathrooms or kitchens. Enamel Undercoat should be applied to walls sealed with latex primer. The use of Enamel Undercoat in this system adds thickness or build to the dry film and prevents a starved appearance that shows unsightly tape joints.

PREVIOUSLY FINISHED SURFACES:

Sand glossy surfaces to a dull finish. Remove all loose and peeling paint by scraping and sand smooth by feathering edges. Liquid deglossers may be used as a surface conditioner to dull glossy surfaces and assure adhesion in place of sanding.

Apply primer undercoat to bare areas or preferably to the entire surface and allow to dry a minimum of 16 hours. Sand lightly and apply topcoat.

MIXING:

Stir each container thoroughly prior to use. Although no reduction is usually required for brush or roller application, mineral spirits can be added if necessary to ease brushing or replace evaporation losses.

DESCRIPTION:

Supr-Covr is a premium quality alkyd-based interior enamel undercoat for use over bare wood, trim, furniture, plaster walls and previously painted surfaces. Product has excellent adhesion and will seal the most porous surfaces providing good holdout for finish coats. Supr-Covr may be topcoated with either latex or oil-based topcoats. Brush application is preferred. Roller or spray application may also be used.

Values based on **Supr-Covr Alkyd Enamel Undercoat White, 0436**

Weight Gallon: 12.11

Weight Solids: 72.6%

Volume Solids: 49.1%

Coverage:

@ 1 Dry Mil: 787 sq. ft./gallon
 @ Spread Rate: 400 sq. ft./gallon (4.0 mils wet)
 Deposits a 2.0 mil dry film

VOC (g/l): Not to Exceed 350

Viscosity: 80-85 K.U. @ 77° F.

Gloss @ 60: 15 Max

Grind (Hegman): #4.5-5

DOT Class: Combustible, Flash Point 103°F.

Federal Specification: TT-E-543 Performance Alternate

HMIS/NFPA: 1,2,0

Cure Time (Based on 70° F. & 50% R.H.):

To Touch: 2 Hours
 To Recoat: Overnight

Recommended Thinner: Water for clean-up and reduction for spray

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Do not take internally. Close container after each use. Use only with adequate ventilation. **KEEP OUT OF THE REACH OF CHILDREN.** For specific safety requirements, refer to the Material Safety Data Sheet.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.