

CLEAN UP:

Clean brushes and equipment with mineral spirits. Dispose of unused paint and waste in accordance with local, state and federal regulations.

COVERAGE:

One gallon of floor enamel will cover 400 square feet (37 square meters per 3.785 liters) per gallon on smooth surface. Rough surfaces will require more paint.

DRYING:

Optimum drying conditions are 60° F. to 90° F. (16° C. to 32° C.) at 50% R.H.

To Touch	4 Hours
To Recoat	16 Hours
For Light Traffic	24 Hours
Full Service	48 Hours

Lower temperatures and high humidity will slow dry.

SUPR-TUFF ALKYD PORCH & FLOOR ENAMEL

5-7

DESCRIPTION:

Supr-Tuff is a highly durable, mar-resistant gloss, alkyd base porch and floor enamel for interior and exterior use. Supr-Tuff is formulated for use on new or previously painted floors and/or stairs constructed of wood, metal and aged concrete. Product may be applied by brush, roller or spray.

Values based on **Supr-Tuff Alkyd Porch & Enamel White, 1450**

Weight Gallon: 9.31

Weight Solids: 63.3%

Volume Solids: 47.5%

Coverage:

@ 1 Dry Mil: 762 sq. ft./gallon

@ Spread Rate: 400 sq. ft./gallon (4.0 mils wet)
Deposits a 1.9 mil dry film

VOC (g/l): Not to exceed 400

Viscosity: 74-78 K.U. @ 77° F.

Gloss @ 60: 90+

Grind (Hegman): #7

DOT Class: Combustible, Flash Point 103°F.

Federal Specification: TT-E-487 Performance Alternate

HMIS/NFPA: 1,2,0

Cure Time (Based on 70° F. & 50% R.H.):

To Touch: 4 hours

To Recoat: Overnight

Recommended Thinner: None. Apply at package viscosity. Mineral spirits for clean-up

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Do not take internally. Close container after each use. Use only with adequate ventilation. **KEEP OUT OF REACH OF CHILDREN.** For specific safety requirements, refer to the Material Safety Data Sheet.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.

Originated: 4/92
Revised: 9/99