

DESCRIPTION:

A rapid drying, clear sealer for new, unfinished wood. It's ease of sanding and excellent hold-out qualities make it the ideal first-coat sealer for both stain and gloss finishing systems. It has been specifically formulated for use under Eventone Urethane Varnish, Eventone Varnish Stain and Eventone Spar Varnish.

Values based on **Eventone Interior Sanding Sealer, 0426**

Weight Gallon:	7.05
Weight Solids:	35.9%
Volume Solids:	28.4%
Coverage:	
@ 1 Dry Mil:	455 sq. ft./gallon
@ Spread Rate:	400 sq. ft./gallon (4.0 mils wet) Deposits a 1.1 mil dry film
VOC (g/l):	Not to exceed 550
Viscosity:	45-55 Sec. #4 Ford Cup @ 77° F.
Gloss @ 60:	35-45
Grind (Hegman):	#6
DOT Class:	Flammable, Flash Point 57°F., UN1263
Federal Specification:	N/A
HMIS/NFPA:	1,3,0
Cure Time (Based on 70° F. & 50% R.H.):	
To Touch:	30 Minutes
To Recoat:	2 Hours

Recommended Thinner: None. Apply at package viscosity. Mineral spirits for clean-up.

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Do not take internally. Close container after each use. Use only with adequate ventilation. **KEEP OUT OF THE REACH OF CHILDREN.** For specific safety requirements, refer to the Material Safety Data Sheet.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.