

DESCRIPTION:

Wondr-Tuff is a premium quality, quick-drying satin finish latex floor paint. Wondr Tuff is especially suited for use on unpainted, etched interior or exterior concrete (new or old) and previously painted or primed wood. Ideal for use on basement floor, steps, porches and factory and warehouse floors. This material has excellent abrasion resistance and will withstand the severe abuse and weathering encountered both in and out of doors. Product features quick dry, water clean-up and easy application with brush, roller or spray.

Reprinted from National Paint and Coatings Association, Inc., FLAMMABILITY OF PAINT STUDY conducted by Southwest Research Institute, Project 3-3774-141. "We believe this study provides substantial evidence that conventional paints and coatings do not increase the flame spread of either non-flammable or flammable substrate upon which they are applied. It also indicates that any fuel contribution or smoke density increase is insignificant when compared with the contribution of the substrate itself."

SPECIAL CAUTIONS:

Keep packaged material from freezing. If material has been frozen, do not stir until completely thawed. If material, when stirred after thawing, is of uniform consistency and has a suitable viscosity with no lumps, it may be used.

Do not apply when surface, air or material temperature is below 50° F. (10° C.).

SURFACE PREPARATION:

GENERAL - Surface must be clean. Remove oil and grease with a detergent solution or paint thinner. Wash off dirt with warm soapy water and rinse with fresh water. Rust should be removed by wirebrushing or sanding. Refer to "**Surface Preparation Guide**" for more detailed instructions.

UNFINISHED SURFACES:

Sand smooth and remove sanding dust. Countersink nails. Apply first coat of Latex Floor Finish and allow to dry for 30 minutes. Putty nail holes. When putty is dry, apply the second coat of floor finish.

MASONRY AND CONCRETE - Slick troweled concrete surfaces should be etched with a 10% solution of Muriatic (Hydrochloric) Acid in water. Allow acid solution to remain on the surface for about 15 minutes. When etching action is complete, flush away remaining acid with large amounts of clean water. Allow surface to dry and remove dust before painting with Latex Floor Finish.

On surfaces where muriatic acid cannot be used to neutralize the efflorescence, sand, scrape, and wire brush and coat with Masonry Conditioner before painting.

Concrete and haydite blocks should be filled with Latex Block Filler. Allow to dry overnight before topcoating.

No primer is necessary on concrete and masonry surfaces.

IRON AND STEEL - Prime with metal primer and allow to dry overnight before topcoating.

PREVIOUSLY FINISHED SURFACES:

Remove all loose and flaking paint by scraping and sanding. All calcimine paints must be removed before painting by scraping and washing. Scuff sand slick, hard glossy surfaces with coarse sandpaper. Liquid deglossers may be used to promote adhesion by softening and dulling the old slick, hard glossy paint and removing grease, wax, etc. Spot prime bare areas with recommended primer and allow to dry before topcoating.

DESCRIPTION:

Wondr-Tuff is a premium quality, quick-drying satin finish latex floor paint. Wondr Tuff is especially suited for use on unpainted, etched interior or exterior concrete (new or old) and previously painted or primed wood. Ideal for use on basement floor, steps, porches and factory and warehouse floors. This material has excellent abrasion resistance and will withstand the severe abuse and weathering encountered both in and out of doors. Product features quick dry, water clean-up and easy application with brush, roller or spray.

Values based on **Wondr-Tuff Latex Floor Enamel**
5650 White, 5645 Battleship Gray, 5657 Tile Red, 5659 Ivy Green
5661 Silver Gray

Weight Gallon: 10.6

Weight Solids: 50.1%

Volume Solids: 36.2%

Coverage:

@ 1 Dry Mil: 581 sq. ft./gallon

@ Spread Rate: 400 sq. ft./gallon (4.0 mils wet)
Deposits a 1.5 mil dry film

VOC (g/l): Not to Exceed 250

Viscosity: 75-80 K.U. @ 77° F.

Gloss @ 60: 5 Max, Flat

Grind (Hegman): #5

DOT Class: Non-Combustible, Not Regulated

HMIS/NFPA: 1,0,0

Cure Time (Based on 70° F. & 50% R.H.):

To Touch: 30 Minutes

To Recoat: 2 Hours

Recommended Thinner: Water for clean-up and reduction for spray

Temperature Resistance: Continuous 150° F., Intermittent 200° F.

CAUTION! Do not take internally. Close container after each use. Use only with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN. For specific safety requirements, refer to the Material Safety Data Sheet. Protect from freezing.

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance, but is subject to change without prior notice. We make no guarantee of any kind, express or implied, including merchantability and fitness for particular purposes. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor, or cost of labor, and other consequential damages are hereby excluded.